

## to you, our customer



0.025mm to 21mm (.001" to .827")



Order 3m to 3t (10 ft to 6000 Lbs)



Delivery: within 3 weeks



Wire to your spec



E.M.S available



Technical support

- Round wire
- Bars or lengths
- Flat wire
- Shaped wire
- Rope/Strand

## **Packaging**

- Coils
- Spools
- Bars or lengths



## STAINLESS STEEL 1.4310





Chemical Composition			Specifications	Key Features	Typical Applications
Element	Min %	Max %	BS EN 10088-3	Good mechanical properties and corrosion	Springs and high strength
С	0.05	0.12	DIN EN 10270-3	resistance	components
Mn	-	2.00		Capable of high tensile strength following	Engineered components
P		0.045		cold work	Chemical processing
P	-	0.045		Magnetic following cold work	Electronic equipment
S	-	0.015	Designations		
Si	-	2.00	W.Nr. 1.4310		
Cr	16.00	19.00	UNS S30100 AWS 131		
Ni	6.00	9.50	7.113 131		
N	-	0.11			
Мо	-	0.80			
Fe BAL					

Density	7.90 g/cm <sup>3</sup>	0.285 lb/in <sup>3</sup>	
Melting Point	1420 °C 2590 °F		
Coefficient of Expansion	17.6 μm/m °C (20 – 100°C)	9.8 x 10 <sup>-6</sup> in/in °F (70 – 212 °F)	
Modulus of Rigidity	76 kN/mm²	11000 ksi	
Modulus of Elasticity	190 kN/mm²	28000 ksi	

Heat Treatment of Finished Parts							
Condition or complied by Alley Wive	Туре	Temperature		Time o (IIIv)	Caalina		
Condition as supplied by Alloy Wire		°C	°F	Time (Hr)	Cooling		
Annealed or Spring Temper	Stress Relieve	250 - 400	480 - 750	1	Air		

Properties						
Can disian	Approx. tensile strength		Approx. operating temperature			
Condition	N/mm²	ksi	°C	°F		
Annealed	<800	<116	-200 to +300	-330 to +570		
Spring Temper	1600 – 2200	232-319	-200 to +300	-330 to +570		

 $\label{thm:continuous} The above tensile strength \ ranges \ are \ typical. \ If you \ require \ different \ please \ ask.$ 





